



Sn42/Bi58 Solid SOLDER WIRE

CORPORATE HEADQUARTERS USA: 315 Fairbank St. Addison, IL † 630-628-8083 FAX 630-628-6543
EUROPE UK: Unit 9 Apex Ct. Bassendale Rd. Bromborough, Wirral CH62 3RE † 44 151 334 0888 † FAX 44 151 346 1408
ASIA-PACIFIC HEADQUARTERS SINGAPORE: 6 Tuas South St. 5 Singapore 637790 † 65 6795 7757 † FAX 65 6795 7767
PHILIPPINES: Phase 1 Qualitek Ave. Mariveles, Bataan Philippines C-2106 † 6347 935 4163 † FAX 63475613717
CHINA: 3B/F, YiPa Print Bldg. 351 # JiHua Rd., Buji Shenzhen, China 518112 † 86 755 28522814 † FAX 86 755 28522787

Physical Properties

Solder Composition

Qualitek Bi58 is designed as a lead-free alternative for Sn/Pb alloys for electronics assembly operations. The Qualitek Bi58 alloy conforms and exceeds the impurity requirements of J-STD-006 and all other relevant international standards.

Typical Analysis													
Sn	Ag	Cu	Pb	Sb	Bi	In	As	Fe	Ni	Cd	Al	Zn	Au
Bal	0.020 Max	0.050 Max	0.050 Max	0.050 Max	57.5- 58.5	0.050 Max	0.010 Max	0.010 Max	0.005 Max	0.001 Max	0.001 Max	0.001 Max	0.002 Max

	Sn42/Bi58	Sn63/Pb37		Sn42/Bi58	Sn63/Pb37
Melting Point, °C	138 E	183 E	Yield Strength, psi	7119	3950
Hardness, Brinell	22HB	14HB	Total Elongation,%	46	48
Coefficient of Thermal Expansion	13.8	24.7	Shear Strength MPa, at 1mm/min 20 °C	27	34.5
Tensile Strength, psi	5400	4442	Shear Strength MPa, at 1mm/min 100 °C	15.6	21.6
Density, g/cc	8.72	8.42	Fatigue Strength, Mpa at 1000 cycles 20 °C	16	16.2
Electrical Resistivity , (μohm-cm)	34.5	14.5	Fatigue Strength, Mpa at 1000 cycles 100 °C	7.9	10.2
Electrical Conductivity, %IACS	4.5	11.9	Specific Heat (J/g)	46	45

Features & Benefits

- Low melting point, prevents thermal degradation of heat sensitive components
- Acceptable wetting & flowing characteristics
- Low to non-toxic lead-free solder

Available Wire Diameters

Diameter/in	0.048*	0.032*
Diameter/mm	1.20	0.80

Storage & Shelf Life

Solder wire storage should be in a 65 - 80°F environment away from direct heat. When handling solder wire, it is recommended to wear appropriate gloves. Solid solder wire has an indefinite shelf life.

Disposal

Sn42/Bi58 Solid Wire solder should be disposed of in accordance with state & local authority requirements.

Packaging

500 gram (0.5 Kilogram) per Box